


In the Claims:

1. (Amended) A method of making a fuser member having a support comprising the steps of:

A) providing a support;

a2 B) coating a coating composition contained in an organic solvent onto the support, thereby forming a layer of the coating composition on said support, said coating composition comprising a fluorocarbon thermoplastic random copolymer, a curing agent having a bisphenol residue, a particulate filler containing zinc oxide, antimony-doped tin oxide particles, and an aminosiloxane, the fluorocarbon thermoplastic random copolymer having subunits of:



wherein

x is from 1 to 50 or 60 to 80 mole percent,

y is from 10 to 90 mole percent,

z is from 10 to 90 mole percent,

x + y + z equals 100 mole percent; and

C) curing said layer of the coating composition on said support for 5 to 10 hours at a temperature in the range of 25°C to 120°C.

a3 4. (Amended) The method of claim 1 wherein the aminosiloxane has a total concentration in the coating composition of from 1 to 20 parts by weight per 100 parts of the fluorocarbon thermoplastic random copolymer.

a4 10. (Amended) The method of claim 1 further comprising:
forming a cushion layer between said substrate and said layer of the coating composition.

Add the following new claims:

a5 21. (New) The method of claim 1 wherein said temperature in step C) is in the range of 25°C to 50°C.

22. (New) The method of claim 21 wherein said temperature in step C) is 25°C.